

Screening effect of interlayer coupling on electronic transport properties of layered high- T_c oxides

Ryoko Sugano, Toshiyuki Onogi, and

Yoshimasa Murayama

Advanced Research Laboratory, Hitachi, Ltd., Hatoyama, Saitama 350-03, Japan

Abstract

We have investigated the effect of thermal fluctuation on the interlayer coupling of three-dimensional Josephson-junction arrays with anisotropic interactions as a model of layered high- T_c oxides, focusing on non-Ohmic current-voltage characteristics. Langevin dynamic simulations were performed for various Josephson-coupling anisotropies and for various temperatures in both zero and finite magnetic fields. We find that, in the highly anisotropic region, the interlayer coupling, which causes the non-vanishing critical current (I_c), is suppressed by thermal fluctuations, and tends to push up the Kosterlitz-Thouless transition temperature (T_{KT}) of the two-dimensional (2D) regime. In this highly anisotropic region, I_c begins to decrease drastically near T_{KT} . This suggests that interlayer coupling is screened by thermally excited 2D small vortex-antivortex pairs as well as the intralayer logarithmic part of vortex-antivortex interactions. Moreover, weak magnetic fields parallel to the c -axis affect only the logarithmic-interaction part between the 2D pancake vortices.

74.60.Ge, 74.40.+k, 74.80.Dm

I. INTRODUCTION

The coherence length (ξ_{ab})-scale thermal fluctuation in high- T_c oxides has been extensively discussed in association with the thermal excitation of two-dimensional (2D) vortex-antivortex pairs. In the strictly 2D case, it is well known that the logarithmic interaction between these vortex-antivortex pairs shows power-law behavior of current-voltage (I - V) characteristics, and leads to the Kosterlitz-Thouless (KT) transition.¹ Recently, the KT transition has been observed even in a one-unit-cell(12Å)-thick YBCO thin film.² This clearly indicates that superconductivity in high- T_c oxides is intrinsically two-dimensional. Under weak magnetic fields, power-law behavior and the KT transition have also been observed in both I - V characteristics and magnetoresistance.³ These observations were also confirmed by numerical simulations of 2D Josephson-junction (JJ) arrays.⁴

On the other hand, high- T_c superconductors in bulk are three-dimensional (3D) weakly coupled stacks of superconducting CuO_2 planes. The existence of a weak but non-zero interlayer Josephson-coupling between CuO_2 layers has been observed.⁵ This coupling could alter the logarithmic interaction between 2D pancake vortices,⁶ thus blunting transition, shifting the Kosterlitz-Thouless transition temperature T_{KT} ,^{7,8} and modifying I - V characteristics.^{9,10} Moreover, the correlation of 2D vortices in adjacent layers is expected to decrease near the transition temperature T_{cr} , and it has been observed that layers are decoupled when $T > T_{cr}$.¹¹⁻¹⁴ It is not yet known whether layers are completely decoupled just below T_{cr} .

In this paper, we systematically investigate the screening effect of the interlayer coupling on the electric transport properties in both zero and weak magnetic fields ($H \parallel c$), and discuss the results based on the KT mechanism.

II. MODEL AND FORMALISM

We start with a 3D anisotropic Josephson-junction (JJ) array regarded as a simple lattice version of a type-II superconductor derived from a Lawrence-Doniach type model.¹⁵ The

Hamiltonian is written as

$$\mathcal{H} = -J_{\perp c} \sum_{\langle i,j \rangle_{\perp c}} \cos(\Delta\theta_{ij} - A_{ij}) - J_{\parallel c} \sum_{\langle k,l \rangle_{\parallel c}} \cos(\Delta\theta_{kl} - A_{kl}), \quad (1)$$

where $\Delta\theta_{ij}$ denotes the superconducting phase difference between nodes i and j . $J_{\perp c}$ and $J_{\parallel c}$ are intralayer (inplane) and interlayer Josephson-coupling energies related to the magnetic penetration depth $\lambda_{\parallel c, \perp c}$, respectively, such that $J_{\parallel c, \perp c} = \Phi_0^2 a / 16\pi^3 \lambda_{\parallel c, \perp c}^2$, and also related to the bare critical current of each Josephson-junction through $I_{0\parallel c, \perp c} = (2e/\hbar) J_{\parallel c, \perp c}$. Here a and Φ_0 are a lattice spacing and flux quantum, respectively. We assume that a is comparable to the inplane coherence length ξ_{ab} . Bare anisotropy ratio $\gamma_0 = \gamma(T=0)$ at $T=0$ is defined as

$$\gamma_0 = \gamma(T=0) = J_{\parallel c} / J_{\perp c} = (\lambda_{\perp c} / \lambda_{\parallel c})^2 \quad (2)$$

At finite temperature, γ_0 can be replaced by effective anisotropy ratio $\gamma(T)$. Magnetic fields are introduced as frustration $2\pi f = A_{ij} + A_{jk} + A_{kl} + A_{li}$ around each plaquette with $A_{ij} = (2e/\hbar c) \int_i^j \mathbf{A} \cdot d\mathbf{l}$ and $f = Ha^2/\Phi_0$. The external DC current I is injected by adding $-(\hbar/2e)I \sum_{\langle i,j \rangle_{\parallel I}} \Delta\theta_{ij}$ to Eq. (1). We directly calculated the I - V characteristics of the $8 \times 8 \times 3$ JJ array for various reduced temperatures $k_B T / J_{\perp c}$, and for various weak magnetic fields, via Langevin simulation technique, as previously reported in Ref[10].

III. VORTEX DYNAMICS

Thermal excitation of 2D vortex-antivortex pairs plays an important role in 2D superconductivity ($\gamma_0 = 0$). Such a 2D vortex pair separated by distance r within the same layer interacts with a logarithmic potential $U_{2D} = E_1 \ln(r/\xi_{ab})$, and leads to the simple power-law I - V characteristics:

$$R = V/I \propto I^{\alpha-1}. \quad (3)$$

Moreover, in this 2D regime, the KT transition may be caused by spontaneous unbinding of vortex pairs due to thermal fluctuation. At the KT transition temperature T_{KT} , the critical

singularity can be observed as a discontinuous jump (called universal jump) from 2 to 0 in the temperature dependence of the power-law exponent $\alpha - 1$. This jump separates the non-Ohmic resistive state ($\alpha - 1 > 2$) for $T < T_{KT}$ from the Ohmic state ($\alpha - 1 = 0$) for $T > T_{KT}$.¹⁶ In the presence of a weak interlayer Josephson-coupling ($\gamma_0 \neq 0$), it should be noted that the interlayer coupling modifies the logarithmic interaction between vortices within the same layer.⁶ The modified vortex-antivortex interaction energy $U_{mod}(r)$ is distinguished by the characteristic size of vortex pairs $r_\gamma(T)$, which is defined by effective anisotropy ratio γ based on Eq. (2):

$$r_\gamma(T) = \xi_{ab}/\sqrt{\gamma(T)}. \quad (4)$$

Here the strong anisotropy regime is defined by $r_\gamma \gg 2a$, i.e., $\sqrt{\gamma} \ll 0.5$, where the thermally excited 2D vortex fluctuations are dominant rather than the 3D vortex loop fluctuations.¹⁰ In this regime ($\sqrt{\gamma} \ll 0.5$), while on the one hand the size r of vortex pairs smaller than r_γ adds the r -square interaction to the logarithmic interaction between vortices,⁸ the larger size ($r \gg r_\gamma$) adds the r -linear interaction.¹¹

$$U_{mod}(r) = E_c + E_1(T) \ln(r/\xi_{ab}) + (1/4)\gamma(T)E_1(T)(r/\xi_{ab})^2 \quad (r \ll r_\gamma) \quad (5)$$

$$= E_c + E_1(T) \ln(r/\xi_{ab}) + (\pi/\sqrt{2})\sqrt{\gamma(T)}E_1(T)(r/\xi_{ab} - 1) \quad (r \gg r_\gamma) \quad (6)$$

Here E_c is the energy to create a 2D vortex in one layer, and $E_1(0) = 2\pi J_{\perp c}$. Compared with the second logarithmic term and the third r -square term in Eq. (5), the logarithmic term is considerably larger than the r -square term, and thus 2D behavior is displayed for the smaller- r regime ($r \ll r_\gamma$). For the larger- r regime ($r \gg r_\gamma$), on the other hand, the r -linear term is of the same order as the logarithmic term in Eq. (6), and we should expect the interlayer Josephson coupling effect to appear clearly in the electric properties.

Considered with the r -linear form of the Lorentz force, this added r -linear interaction, based on large-size vortex pair excitations, modifies the I - V characteristics with non-vanishing critical current I_c in the larger- r regime,⁹ and this is supported by numerical simulations of 3D anisotropic JJ arrays.¹⁰

$$R \propto (I - I_c)^{\alpha-1}. \quad (7)$$

Here,

$$I_c \sim \sqrt{\gamma(T)} c E_1(T) / \Phi_0 \xi_{ab} \quad (8)$$

and

$$\alpha - 1 \sim E_1(T) / k_B T \quad (9)$$

are required. In strongly anisotropic BSCCO with $\gamma \sim 4 \times 10^{-4}$, $r_\gamma \sim 1000 \text{ \AA}$ is significantly large, and almost pure 2D behavior is expected to appear. On the other hand, in less anisotropic YBCO with $\gamma \sim 4 \times 10^{-2}$, $r_\gamma \sim 100 \text{ \AA}$, and this much smaller value of r_γ is considered to greatly enhance the r -linear term, even for the 10-unit-cell(120 $\text{\AA}$)-thick film.

Focusing on this larger- r regime, we below studied the effect of the interlayer coupling on the electric properties in zero and finite magnetic fields for various finite temperatures. In particular, we will discuss the power-law I - V characteristics with a non-vanishing critical current I_c and the power-law exponent $\alpha - 1$ in Eqs. (7)-(9), which eventually result in $\sqrt{\gamma(T)}$ and $E_1(T)$ renormalized with the screening effect of the interlayer coupling by 2D vortex-antivortex fluctuations in the weak coupling regime.

IV. RESULT AND DISCUSSION

The inset of Fig. 1 shows log-log plots of I - R ($R = V/I$) curves for various reduced temperatures $k_B T / J_{\perp c}$ at $H = 0$ and $\gamma_0 = 0.04$. On the low temperature side ($k_B T / J_{\perp c} \leq 0.7$), I - R curves display a negative curvature, and seem to obey the modified power-law with a non-vanishing critical current I_c in Eq. (7), whereas, in the higher temperature regime ($k_B T / J_{\perp c} \geq 0.7$), they tend to accord with the simple power-law relationship in Eq. (3). Also, in this high temperature regime the power-law exponent $\alpha - 1$ seems to be smaller than 2. We can also see this feature more clearly by replotting these curves together with Eq. (7) as depicted in Fig. 1. Here the dotted lines are fitted for each I - R curve using on

χ^2 fit based on Eq. (7). The I - R curves seem classified into two groups. One group, for $k_B T/J_{\perp c} \leq 0.7$, has non-Ohmic power-law behavior with a non-vanishing critical current I_c and with an exponent which $\alpha - 1$ larger than 2. The other is for $k_B T/J_{\perp c} \geq 0.7$ and displays nearly Ohmic power-law behavior for $\alpha - 1 < 2$.

In the presence of external current, the modified interaction energy between two vortices from Eq. (6) is written by

$$U_{mod}(r) = E_c + E_1 \ln(r/\xi_{ab}) + E_2(r/\xi_{ab} - 1) - (\Phi_0/c)Ir \quad (10)$$

$$\sim E_c + E_1 \ln(r/\xi_{ab}) - (\Phi_0/c)(I - I_c)r, \quad (11)$$

where $E_2 = \sqrt{\gamma}E_1$. For the strictly 2D case at $\gamma(T) = 0$, the third term in Eq. (10) vanishes because $E_2 = 0$, and Eq. (10) results in the pure 2D interaction of the logarithmic form.¹⁶

Due to the third term in Eq. (11) for $\gamma_0 \neq 0$, current-induced unbinding of 2D vortex pairs are suppressed by

$$I_c = E_2(c/\xi_{ab}\Phi_0) = \sqrt{\gamma}E_1(c/\Phi_0\xi_{ab}). \quad (12)$$

The maximum value of U_{max} and the maximum size r_{max} ($U_{max} = U_{mod}(r_{max})$), that give the thermal activation rate Γ from bound pairs to free vortices by $\Gamma \propto e^{-U_{max}/k_B T}$, become larger than in the 2D case. Therefore the resistivity is suppressed in the presence of the interlayer coupling.

Figure 2 (a) shows the temperature dependence of I_c for various values of bare anisotropy ratio γ_0 at $H=0$. I_c decreases with increase in temperature. In particular, I_c vanishes in the high temperature region for the extremely weak coupling ($0 < \gamma_0 < 0.1$). The effect of the interlayer coupling is suppressed by thermal fluctuations, and vanishes to zero. When we compare the I - R curves and the temperature dependence curve of I_c for $\gamma_0 = 0.04$, we can see that Ohmic characteristics with $\alpha - 1 < 2$ appear in the region where I_c vanishes. There are two different ranges distinguished by temperature T_{Ic} with $I_c(T > T_{Ic}) = 0$. Moreover I_c is extremely suppressed just below T_{Ic} . These regions are believed to be associated with the KT transition, as we will discuss later.

In the temperature dependence of $\alpha - 1$ as shown in Fig. 2 (b), we can see a kink-like anomaly in the curve for the 2D case ($\gamma_0 = 0$) around $\alpha - 1 = 2$. A discussion of this anomaly was based on the KT vortex-antivortex unbinding transition corresponding to a sign for the universal jump.¹⁶ For the modest-size ($8 \times 8 \times 3$) lattice, unfortunately, numerical evidence for the KT singularity is inconclusive, since the universal jump is expected to broaden largely, according to $\Delta T \propto 1/\ln(L)$ with linear size L . From the numerical data, we extract the KT transition temperature T_{KT}^{2D} , tentatively determined by the exponent $\alpha(T_{KT}^{2D}) - 1 = 2$ for the 2D case at $\gamma_0 = 0$. Even for the weak coupling case ($0 \neq \gamma_0 < 0.1$) we also see the analogous kink-like anomalies around $\alpha - 1 = 2$. This suggests that the KT transition would survive in the presence of such a weak interlayer coupling. The temperature at the anomaly $T_{KT}^{3D}(\gamma_0 \neq 0)$ seems to increase monotonically with increasing γ_0 . Moreover, each T_{KT}^{3D} corresponds to each vanishing temperature T_{Ic} in the temperature dependence of I_c (Fig. 2 (a)), that is, the KT anomaly appears at the time I_c vanishes ($T_{KT}^{3D}(\gamma_0) = T_{Ic}(\gamma_0)$ for $\gamma_0 \neq 0$). Since $I_c(T) \propto E_2(T)$, both the intralayer logarithmic interaction part $E_1(T)$ and the interlayer r -linear part $E_2(T)$ of Eq. (10) must be screened by 2D vortex-antivortex fluctuations. This screening effect of vanishing to zero of $E_2(T)$ above T_{KT}^{3D} is consistent with Monte Carlo results by Minnhagen et. al.¹¹ It is suggested that the system is anisotropic 3D below T_{KT}^{3D} and is 2D just above T_{KT}^{3D} ($E_2(T) \neq 0$ for $T < T_{KT}^{3D}$, and $E_2(T) = 0$ for $T > T_{KT}^{3D}$).

Note that there are plateau regions in the temperature dependence of $\alpha - 1$ just below T_{KT}^{3D} for the case with the non-zero interlayer coupling. The size of the plateau becomes larger with the increase of the interlayer coupling. The plateau begins at the KT anomaly temperature T_{KT}^{2D} without the interlayer coupling around $\alpha - 1 = 2$. Just above that temperature T_{KT}^{2D} , I_c begins to decrease drastically with increase in temperature. This rapid decrease in I_c can be regarded as the drastic suppression of effective anisotropy ratio $\gamma(T)$. This is confirmed by seeing the temperature dependence of $\sqrt{\gamma(T)}$ given by the ratio of the exponent $\alpha - 1$ to the critical current I_c :

$$\sqrt{\gamma(T)} \sim \frac{E_2(T)}{E_1(T)} = \frac{\Phi_0 \xi_{ab}}{ck_B} \frac{I_c}{(\alpha - 1)T}. \quad (13)$$

Here we use Eq. (9) and Eq. (12). Figure 3 shows the temperature dependence of our extracted value of $\sqrt{\gamma(T)}$ in Eq. (13) at $H = 0$ for various bare anisotropy ratios γ_0 . We can see temperature independent behavior in the low temperature phase ($T < T_{KT}^{2D}$), i.e., $\gamma(T)$ has a constant value below T_{KT}^{2D} . This implies that below T_{KT}^{2D} both $E_2(T)$ and $E_1(T)$ are renormalized with the same form, and effective anisotropy ratio $\gamma(T)$ is not screened ($\gamma(T) = \gamma_0$ for $T < T_{KT}^{2D}$). $\gamma(T)$ begins to decrease toward zero above T_{KT}^{2D} . The rapid decrease of $\gamma(T)$ in the high temperature region agrees with Pierson's Renormalization Group (RG) study¹⁷ including the screening due to small intralayer 2D vortex pairs. Small 2D vortex pairs in each plane are also relevant to the weakening of the r -linear part of the interaction in the high temperature phase, where the logarithmic part of the interaction is fully renormalized. This also indicates that correlation along the c -axis is reduced.

The qualitative change around T_{KT}^{3D} is interpreted as a sort of dimensional crossover from anisotropic 3D vortex fluctuations caused by the Josephson coupling between layers to pure 2D vortex fluctuations of the decoupled regime. The decoupled regime above T_{KT}^{3D} exhibits Ohmic-behavior, while non-Ohmic power-law I - R curves of $R \propto (I - I_c)^{\alpha-1}$ appear in the weak coupling regime below T_{KT}^{3D} . Due to the modest-size ($8 \times 8 \times 3$) lattice, our calculated power-law exponent $\alpha - 1$ is not exactly 0, but $\alpha - 1 < 2$, in the decoupled regime. Nevertheless here it is interesting that smaller vortex pairs reduced both interlayer r -linear and intralayer logarithmic interactions between 2D vortex pairs; full renormalization of the logarithmic part of interaction seems to be a trigger for reduction of the r -linear part of the interaction.

We can also see the power-law behavior of I - R curves, fitted with Eq. (7), even in the weak magnetic field at $k_B T / J_{\perp c} = 0.6$ and $Ha^2 / \Phi_0 = 0.0104$, in Fig. 4 (a). Log-plus r -linear interaction between 2D vortex pairs survives even in the magnetic field. Moreover, there is other power-law behavior in magnetoresistance, as depicted in Fig. 4 (b), at $k_B T / J_{\perp c} = 0.6$ and $I / I_{0\perp c} = 0.4$.

$$R \propto H^\beta \quad (14)$$

The coexistence of two power-law behaviors (Eq. (7) and Eq. (14)) leads mathematically to the logarithmic dependence of the power-law exponent $\alpha - 1$ on the magnetic fields as in Fig. 5: $\alpha - 1 \propto \ln 1/H$.^{3,4} The external field suppresses the exponent $\alpha - 1$ through the logarithmic function of the magnetic field Ha^2/Φ_0 . The focusing points appeared in both magnetoresistance and the magnetic field dependence of the exponent $\alpha - 1$. These focusing points have the almost same value of Ha^2/Φ_0 of the order of 0.015. With our assumption that $a \sim \xi_{ab}$, $\xi_{ab} = 12 \text{ \AA}$ in YBCO gives $H \sim 20 \text{ T}$, and $\xi_{ab} = 38 \text{ \AA}$ in BSCCO gives $H \sim 2 \text{ T}$. This suggests that the power-law behavior in YBCO is kept up under ten times higher magnetic fields than that in BSCCO. This is consistent with experimental results.³ In the weak-field regime $Ha^2/\Phi_0 < 0.015$ (Fig. 4 (b) and Fig. 5), the picture in terms of field-induced unbinding of 2D vortex pairs is relevant even in the strongly anisotropic system ($\sqrt{\gamma_0} < 0.5$). The inset of Fig. 5 shows effective anisotropy ratio $\sqrt{\gamma(T)}$ at $k_B T/J_{\perp c} = 0.6$ as a function of Ha^2/Φ_0 . As the magnetic field increases, square-root effective anisotropy ratio $\sqrt{\gamma(T, H)} \sim E_2(T, H)/E_1(T, H)$ seems to increase slightly, at $k_B T/J_{\perp c} = 0.6$. From the relation $\alpha - 1 = E_1(T, H)/k_B T$ in Eq. (9), it is suggested that the external field suppresses only the logarithmic part of interaction $E_1(T, H)$, and maintains or enhances the r -linear part due to the interlayer coupling $E_2(T, H) \simeq \sqrt{\gamma(T, H)} E_1(T, H)$. We can also see this tendency in Fig. 6, where $I_c \propto E_2$ certainly obeys the $\sqrt{\gamma(T, H)}$ -dependence, and $E_1(T, H)$ (the slope of the curve) screened by the magnetic field is expected to give a larger value of $\sqrt{\gamma(T, H)} \sim E_2(T, H)/E_1(T, H)$ than that in the absence of the field. As a result, effective anisotropy ratio $\gamma(T)$ seems to be enhanced in the γ -constant phase ($T < T_{KT}^{3D}(\gamma_0, H)$), that is, the weak magnetic field would apparently strengthen the interlayer coupling. From this larger value of $\gamma(T)$, we expect to find that the plateau in the temperature dependence of $\alpha - 1$, where I_c drastically decreases, is larger under the weak magnetic field than in the absence of any field. Because of this clearer plateau, the universal jump could survive in the magnetic field, as observed experimentally.³

In summary, we have performed Langevin simulations of the 3D anisotropic JJ arrays for a model of layered high- T_c oxides. We found that the effect of vortex fluctuation due to small inplane vortex pairs effectively weakens the interlayer coupling and wipes it out, that is, effective anisotropy ratio $\gamma(T)$ is screened by thermally excited 2D vortex-antivortex pairs in each layer. Just above T_{KT}^{3D} , layers are decoupled, and the system becomes 2D. This is consistent with Monte Carlo study by Minnhagen and Olsson¹¹ and with RG study by Pierson¹⁷. Signs of the transition seem to appear around the temperature T_{I_c} where the critical current I_c vanishes. Moreover, we can see that $T_{KT}^{3D}(\gamma_0)$ tends to shift slightly up in the high temperature direction for small $\gamma_0 \neq 0$. When the interlayer coupling becomes small for $0 < \gamma_0 < 0.1$, I_c vanishes in the high temperature region, and this vanishing of I_c may play a role in triggering the KT transitions. Since $\gamma(T)$ drastically decreases with increase in temperature just below T_{KT}^{3D} , such a weakening effect of the interlayer coupling must mainly be due to screening by the high density of 2D vortex pairs. Thus, at around $T_{KT}^{3D} = T_{I_c}$, there appears a sort of dimensional crossover from the 3D anisotropic system to the pure 2D system. Magnetic fields affect only the logarithmic interaction between 2D vortex-antivortex pairs. In our simulation, we have not introduced the effect of the coherence length ξ_c . Near T_c , significant growth of ξ_c beyond the spacing between CuO_2 layers is expected to give less anisotropic or isotropic 3D behavior far above T_{KT}^{3D} for $\sqrt{1/(1 - T/T_c)} \gg 1$. The KT transition observed in YBCO appears to be a sort of dimensional crossover from the anisotropic 3D system to the strict 2D system, while the one observed in BSCCO is the typical KT vortex-antivortex unbinding transition in the pure 2D system. At that point, YBCO in bulk can be distinguished from BSCCO.

ACKNOWLEDGMENTS

We are grateful to Prof. S. Hikami, Prof. Matsuda, Prof. H. Kawamura, Dr. T. Ohta, and Dr. Hirao for fruitful discussions. Numerical calculations were carried out on a HITAC S-820 supercomputer at the Advanced Research Laboratory of Hitachi, Ltd.

REFERENCES

- ¹ J. M. Kosterlittz and D. J. Thouless, J. Phys. **C 6**, 1181 (1973); B. I. Halperin and D. R. Nelson, J. Low Temp. Phys. **B36**, 599 (1979).
- ² Y. Matsuda, et. al., Phys. Rev. Lett. **69**, 3288, (1992); T. Terashima et al., Phys. Rev. Lett. **67**, 1362 (1991).
- ³ S. Martin et al, Phys. Rev. Lett. **62**, 677 (1989); M. Ban, T. Ichiguchi, and T. Onogi, Phys. Rev. **B40**, 4419(1989); T. Onogi, T. Ichiguchi, and T. Aida, Solid State Commun. **69**, 991(1989).
- ⁴ R. Sugano, T. Onogi, and Y. Murayama, Phys. Rev. **B45**, 10789 (1992); R. Sugano, T. Onogi, and Y. Murayama, Physica **C 185-189**, 1643 (1991).
- ⁵ D. E. Farrell et al., Phys. Rev. Lett. **63**, 782 (1989); R. Kleiner et al., Phys. Rev. Lett. **68**, 2394 (1992).
- ⁶ V. Cataudella and P. Minnhagen, Physica **C 166**, 442 (1990); S. N. Artemenko and A. N. Krugluy, Physica **C173**, 125 (1991), M. V. Feigelman, et al., Physica **C167**, 177 (1990).
- ⁷ Y. Matsuda, et. al., Phys. Rev. **B48**, 10489, (1993); T. Ota, et al., Phys. Rev. **B50**, 3363, (1994).
- ⁸ S. Hikami and T. Tuneto, Prog. Theor. Phys. **63**, 387 (1980).
- ⁹ H. J. Jensen and P. Minnhagen, Phys. Rev. Lett. **66**, 1630 (1991).
- ¹⁰ R. Sugano, T. Onogi, and Y. Murayama, Phys. Rev. **B48**, 13784 (1993).
- ¹¹ P. Minnhagen and P. Olsson, Phys. Rev. **B44**, 4503 (1991); P. Minnhagen and P. Olsson, Phys. Rev. Lett. **67**, 2596 (1991).
- ¹² A. Schilling, et al., Phys. Rev. Lett. **71**, 1899 (1993).
- ¹³ Yu. Eltsev, W. Holm, and O. Rapp, Phys. Rev. **B49**, 12333 (1994).

¹⁴ H. Safer, et al., Phys. Rev. **B46**, 14238 (1992).

¹⁵ W. E. Lawrence and S. Doniach, in *Proceedings of LT12, Kyoto, 1970*, edited by E. Kanda (Keigaku, Tokyo, 1971), p. 361.

¹⁶ A. M. Kadin, K. Epstein, and A. M. Goldman, Phys. Rev. **B27**, 6691 (1983).

¹⁷ S. W. Pierson, Phys. Rev. Lett. **73**, 2596 (1994).

FIGURES

FIG. 1. Resistance $R = V/I$ as a function of $I - I_c$ at $\gamma_0 = 0.04$ for various values of reduced temperature $k_B T/J_{\perp c} = 0.6$ in the absence of a magnetic field. Inset: resistance R as a function of external current I .

FIG. 2. Temperature-dependence for various values of bare anisotropy ratio γ_0 : (a) Critical current I_c as a function of temperature $k_B T/J_{\perp c}$, (b) Power-law exponent $\alpha - 1$ as a function of temperature $k_B T/J_{\perp c}$.

FIG. 3. Temperature dependence of $E_2(T)/E_1(T)$ for various values of bare anisotropy ratio γ_0 . ($E_2(T)/E_1(T)$ is proportional to the square-root of $\gamma(T)$)

FIG. 4. Power-law type behavior for various values of bare anisotropy ratio γ_0 at $k_B T/J_{\perp c} = 0.6$: (a) Power-law magnetoresistance at current $I/I_0 = 0.4$, (b) Power-law type I - R curves at magnetic field $Ha^2/\Phi_0 = 0.0104$.

FIG. 5. Logarithmic behavior of the power-law exponent $\alpha - 1$ at $k_B T/J_{\perp c} = 0.6$; the exponent $\alpha - 1$ as a function of magnetic field Ha^2/Φ_0 . Inset: E_2/E_1 as a function of Ha^2/Φ_0 .

FIG. 6. Anisotropy dependence at $k_B T/J_{\perp c} = 0.6$ for various magnetic fields; critical current I_c as a function of $\sqrt{\gamma(T)}$ with effective anisotropy $\gamma(T)$.